

SPECIFICATION DATA SHEET

100% Non-asbestos Sealing Material

TL1515

F729990E39M9

Description

TL1515 is a gray color high performance vulcanized gasket material. It contains aramid fiber and nitrile butadiene rubber binder with excellent oil-resistance and gas sealing performance. It is intended for high temperature/and high pressure application with short duration maximum temperature up to 290°C (550°F).

Technical Specifications

| Properties | Test Method | Specification | |
|---|--------------------------|---------------|-----|
| Density/ (g/cm ³) | ASTM F1315 | ≥1.45 | |
| Tensile Strength/ (Mpa) | ASTM F152 | ≥11 | |
| Compressibility/% | ASTM F36 | 7 ~ 17 | |
| Recovery/% | ASTM F36 | ≥50 | |
| Stress Relaxation/% | ASTM F38 | ≤35 | |
| Fluid Resistance (Immersion at ASTM IRM 903 Oil, 149±2°C, 5h) | Weight Increase/% | ASTM F146 | ≤22 |
| | Thickness Increase/% | ASTM F146 | ≤18 |
| Fluid Resistance (Immersion at ASTM Fuel B, 21~30°C, 5h) | Weight Increase/% | ASTM F146 | ≤20 |
| | Thickness Increase/% | ASTM F146 | ≤18 |
| Rubber Binder Type | Nitrile Butadiene Rubber | | |

Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.
ASTM F104 (F729990E39M9)

Specification Data Sheet
Revised 09/01/2015

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact with Teamful Sealing.



Chengdu Teamful Gasket Technology Co.,Ltd.

ADD: No.123, Shuanghua Road Sec.3,
Xihanggang Economic Development
Zone, Shuangliu, Chengdu, Sichuan,
P.R.China 610207
Tel: 86-028- 85651020
Fax: 86-028- 85651433
Email: sales@teamful.net

Jiangmen Teamful Sealing Technology Co.,Ltd.

ADD: Zetang Road, Chuanglilai Industrial
Zone, Daze Town, Xinhui District,
Jiangmen City, Guangdong, P.R.China
TEL: 86-0750-6805518
FAX: 86-0750-6805518
Email: sales@teamfulgd.net

Global Trade Contact

Tel: 86-028- 85875509
Fax: 86-028- 85651433
Email: export@teamful.net

天府密封科技
TEAMFUL SEALING

(SINCE)1985

www.teamful.net

www.teamfulseal.com